



TEST REPORT

DATE: 01/05/2004

TEST NUMBER: 093006

CLIENT	Sport Surface Specialties
--------	---------------------------

TEST METHOD CONDUCTED	ASTM F1292-04 Specification for Impact Attenuation of Surface Systems Under and Around Playground Equipment
-----------------------	---

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Dura Turf PNP 1"
COLOR	-----
ROLL	-----
CONSTRUCTION	Rubber

GENERAL PRINCIPLE

A test specimen is impacted at a specified velocity with a missile of given mass and geometry. A transducer mounted in the missile monitors the acceleration time history of the impact, which is recorded with the aid of an oscilloscope or other recording device. The 10 lb. missile was dropped at the appropriate height. The GMAX values, HIC (head impact criteria) are recorded for three drops. The second and third drops are averaged. Testing was conducted at three temperatures as listed on the results. The maximum criteria for passing a drop height is 200 gmax or 1,000 HIC.

TEST RESULTS

Drop Height 3'6" @ 70°F	Drop 1	Drop 2	Drop 3	Avg of 2 nd & 3 rd Drops
G-MAX	176	178	169	173.5
Head Injury Criteria	880	891	795	843

Drop Height 3'6"@ 20°F	Drop 1	Drop 2	Drop 3	Avg of 2 nd & 3 rd Drops
G-MAX	183	194	197	195.5
Head Injury Criteria	869	955	992	973.5

Drop Height 3'6" @ 120°F	Drop 1	Drop 2	Drop 3	Avg of 2 nd & 3 rd Drops
G-MAX	169	174	179	176.5
Head Injury Criteria	844	872	909	890.5

COMMENTS

The submitted sample does not exceed the maximum HIC (1000) or GMAX (200) from drops at the height of 3'6".

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.